

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>P.D. Collier</u>		Lease <u>FWY State</u>		Well # <u>56</u>	
Location of Well	Unit <u>C</u>	Section <u>1</u>	Township <u>1</u>	Range <u>1</u>	County <u>1</u>
Drilling Contractor <u>Co. Tools</u>			Type of Equipment <u>Cable Tool</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>8</u>	<u>7"</u>	<u>23</u>	<u>USED</u>	<u>314</u>	<u>100</u>

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
(Approved) (Rejected) \_\_\_\_\_

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole \_\_\_\_\_ Size of Casing \_\_\_\_\_ Sacks cement required \_\_\_\_\_

Type of Shoe used \_\_\_\_\_ Float collar used \_\_\_\_\_ Btm 3 jts welded \_\_\_\_\_

TD of hole 418 Set \_\_\_\_\_ Feet of \_\_\_\_\_ Inch \_\_\_\_\_ # Grade \_\_\_\_\_

New-used csg. @ \_\_\_\_\_ with 100 sacks neat cement around shoe

+ \_\_\_\_\_ sax \_\_\_\_\_ additives \_\_\_\_\_

Plug down @ 7 pm (AM) (PM) Date 5-24-62

Cement circulated no No. of Sacks \_\_\_\_\_

Cemented by Denton Witnessed by Loblay

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: Cement came to the top on the first job but fell back down the hole. 5-25-62 Circulation was completed with 25 sks pumped in from top of hole and cement stayed there 8 hr