

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>John P. H. Corp.</i>		Lease <i>Larry J</i>		Well # <i>3</i>	
Location of Well	Unit <i>23.6 N</i>	Section <i>22</i>	Township <i>17</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor <i>Cartier Drilling Co.</i>		Type of Equipment <i>rotary</i>			
APPROVED CASING PROGRAM <i>4-23-71</i>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>9 7/8</i>					
<i>11.50</i>	<i>7</i>	<i>20</i>		<i>1150</i>	<i>One</i>
	<i>4 1/2 x 5 1/2</i>	<i>9.5 x 15.5</i>		<i>1500</i>	<i>One</i>
Casing Data: <i>Spec. 12:30 PM 4-23-71 16" - 120 gr - 50 + 4 yds. Reel by mfg.</i>					
Surface <i>28</i> joints of <i>7</i> inch <i>23</i> # Grade <i>N-80</i> <i>used</i>					
(Approved) (Rejected)					
Inspected by <i>Gressett</i> date <i>4-23-71</i>					
Cementing Program <i>7/136 DFM 24 gr.</i>					
Size of hole <i>9 7/8</i> Size of Casing <i>7</i> Sacks cement required					
Type of Shoe used <i>Guide</i> Float collar used <i>no.</i> Btm 3 jts welded <i>third set</i>					
TD of hole <i>1136</i> Set <i>1124</i> Feet of <i>7</i> Inch <i>23</i> # Grade <i>N 80</i>					
New-used csg. @ <i>1124</i> with <i>100</i> sacks neat cement around shoe					
+ <i>300</i> sacks <i>Incor 220 gel</i> additives + <i>6" Silicate - Flocc</i> + <i>220 CC</i>					
Plug down @ <i>9:25</i> (AM) (PM) Date <i>4-30-71</i>					
Cement circulated <i>yes</i> No. of Sacks <i>15054</i>					
Cemented by <i>Danton</i> Witnessed by <i>Gressett</i>					
Temp. Survey ran @ (AM) (PM) Date top cement @					
Casing test @ <i>3:30</i> (AM) (PM) Date <i>5-1-71</i>					
Method Used Witnessed by					
Checked for shut off @ (AM) (PM) Date					
Method used Witnessed by					
Remarks:					