

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Water Pk. Corp.</u>		Lease <u>J. Lamy J</u>		Well # <u>4</u>	
Location of Well	Unit <u>14505</u> <u>330C</u>	Section <u>22</u>	Township <u>17</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor <u>Cactus Drilling Co.</u>			Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM approved 4-5-71

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>9 7/8" @ 700</u> <u>9" @ 1150</u>	<u>7"</u>	<u>20"</u>		<u>1150</u>	<u>line</u>
<u>6 1/4"</u>	<u>4 1/2" x 5 1/2"</u>	<u>9.5" - 15.5"</u>		<u>1500</u>	<u>line</u>

Casing Data: 10 3/4" - 125-505X + 2yds.

Surface 38 joints of 7" inch 20" # Grade H-40 S API

used (Approved) (~~Rejected~~)

Inspected by Gressett date 5-3-71

Cementing Program

Size of hole 9 7/8" Size of Casing 7" Sacks cement required

Type of Shoe used Guide Float collar used Btm 3 jts welded Shroud Sh

TD of hole 1157 Set 1132 Feet of 7 Inch 20 # Grade

New used csg. @ 1120 with 100 sacks neat cement around shoe
+ 300 sacks Incor 2700 lb additives Flowac - Silsonite 2700 CC

Plug down @ 8:30 (~~AM~~) (PM) Date 5-4-71

Cement circulated no No. of Sacks

Cemented by Denton Witnessed by Gressett

Temp. Survey ran @ 5:45 (AM) (PM) Date 5-5-71 top cement @ 420 ⁷² 820

Casing test @ 10:10 (~~AM~~) (PM) Date 5-5-71

Method Used Witnessed by Gressett

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: LC @ 843 Could not get pipe on bit due to cavings Centralizers @
1037, 7'8" + 651 Sack @ 683 + 780 - ran 1" to 440 Pumped + worked for 1 hour
Could not get any deeper - Cemented w/ 75 SX Incon + 3* Flowac + 4% CC in
at 8:30 AM. 5-5-71 no circ. will tag @ 1:00 PM. 1" to 400' + tried to
circ hole with mud no luck Cemented w/ 100 SX as above in @ 3:20 PM.
1" to 385 picked up to 358 + 75 SX as above in @ 7:45 PM. 1" to 240 picked
up to 200' + 100 SX as above in @ 10:40 PM. 5-5-71 no circ.
Ordered out 4 yds of ready-mix to finish filling to surface.
used 3 3/4 yds.