

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWING NO
ARTESIA, NEW MEXICO

105

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Walter P. Hargis</u>		Lease <u>Granger A1</u>		Well # <u>6</u>	
Location of Well	Unit <u>2310N</u> <u>105E</u>	Section <u>23</u>	Township <u>17</u>	Range <u>2-S</u>	County <u>El Paso</u>
Drilling Contractor <u>Cactus Drilling Co.</u>			Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM 4-12-71

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
9 1/2"	7"	26		11-16	2.1
6 7/8"	4 1/2"	25.5 + 1.5"		1500	6.1

Casing Data: 1030-219-

Surface 23 joints of 7 inch 23126 # Grade S-80

4/25 (Approved) (Rejected)

Inspected by O. H. Hargis date 5-28-71

Cementing Program

Size of hole 9" Size of Casing 7 Sacks cement required 7

Type of Shoe used TEAR Float collar used — Btm 3 jts welded RENO-2.0K

TD of hole 1166 Set 1147 Feet of 7 Inch 23126 # Grade N-80 + J-55

Now used csg. @ 1132 with 75 sacks neat cement around shoe

+ 250 sax INACOR MIX additives 750# FLOCELLE + 150# GILSONITE

Plug down @ 500 (PM) Date 6-1-71 2% cal. Chisel

Cement circulated NO No. of Sacks —

Cemented by DEMONT Witnessed by O. H. Hargis

Temp. Survey ran @ 100 (AM) (PM) Date 6-2-71 top cement @ 430'

Casing test @ 1015 (AM) (PM) Date 6-2-71

Method Used 500# Witnessed by —

Checked for shut off @ 100 (PM) Date 6-2-71

Method used 400# Pressure Witnessed by O. H. Hargis

Remarks: LOST CIR. @ 768-771'

1' to 340' 75 SX in @ 2 AM

RAN 50 SX of NEAT CEMENT @ 6° am from SURFACE

RAN 24 ARDS of RUDY MIX @ 8:30 PM

~~23126~~