

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>JATIS PET. CORP</u>		Lease <u>JACKSON EST B4</u>		Well # <u>4</u>	
Location of Well	Unit <u>E</u> <u>2310N</u> <u>990-00</u>	Section <u>22</u>	Township <u>17</u>	Range <u>22</u>	County <u>EDDY</u>
Drilling Contractor <u>PHETUS DRILLING CO.</u>			Type of Equipment <u>ROTARY</u>		
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	Not or <u>Used</u>	Depth	Sacks Cement
<u>13 3/4</u>	<u>10 3/4</u>	<u>32</u>		<u>400</u>	<u>CIP</u>
<u>9 7/8</u>	<u>7"</u>	<u>20</u>		<u>1150</u>	<u>CIRC</u>
<u>6 1/8</u>	<u>4 1/2 + 5 1/2</u>	<u>9.5 + 14"</u>		<u>1500</u>	<u>"</u>
Casing Data:					
Surface <u>31</u> joints of <u>7"</u> inch <u>20</u> # Grade <u>J-55</u>					
✓ (Approved) (Rejected)					
Inspected by <u>O. L. Howe</u> date <u>8-12-71</u>					
Cementing Program					
Size of hole <u>9 7/8"</u> Size of Casing <u>7"</u> Sacks cement required					
Type of Shoe used <u>TEXAS</u> Float collar used <u>Btm 3 jts welded</u> <u>THREAD LOCK</u>					
TD of hole <u>1144</u> Set <u>1131</u> Feet of <u>7</u> Inch <u>20</u> # Grade <u>J-55</u>					
Not used csg. @ <u>1131</u> with <u>175</u> sacks neat cement around shoe					
+ <u>200</u> sack <u>MIX</u> + additives <u>600# FLO SEAL</u> <u>1200# GILSONITE</u>					
Plug down @ <u>10"</u> (PM) Date <u>8-13-71</u>					
Cement circulated <u>NO</u> No. of Sacks					
Cemented by <u>DENTON</u> Witnessed by <u>O. L. Howe</u>					
Temp. Survey ran @ <u>630</u> (AM) (PM) Date <u>8-14-71</u> top cement @ <u>590'</u>					
Casing test @ <u>400</u> (AM) (PM) Date <u>8-14-71</u>					
Method Used <u>500 #</u> Witnessed by					
Checked for shut off @ <u>530</u> (PM) Date <u>8-14-71</u>					
Method used <u>500 #</u> Witnessed by <u>O. L. Howe</u>					
Remarks: <u>TEMP. SHOWED SOME CEMENT @ 520'</u>					
<u>RPH 75 SX FROM SURFACE</u>					
<u>740S 9 READY-MIX.</u>					

CEMT. @ 1028, 810, 589'

BASRET @ 757' - 557'