

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Gates Petr Corp.</u>		Lessee <u>Halliburton DA Com.</u>		Well # <u>1</u>	
Location of Well	Unit <u>N</u> <u>6603</u> <u>2040 W</u>	Section <u>3</u>	Township <u>17</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>And</u>		Type of Equipment <u>Rotary to start down.</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8" or 12 3/4"</u>	<u>48</u>		<u>400</u>	<u>Circ.</u>
<u>12 1/4"</u>	<u>8 3/8"</u>	<u>24</u>		<u>1350</u>	<u>Circ.</u>
<u>7 7/8"</u>	<u>4 1/2" or 5 1/2"</u>	<u>10.5-11.6</u>		<u>8500</u>	<u>250</u>

Casing Data: 15.5 + 17"

Surface 32 joints of 8 3/8 inch 24 # Grade J-55 - 57C

(Approved) (Rejected)

Inspected by J. H. W. W. W. date 12-31-73

Cementing Program

Size of hole 12 1/4" Size of Casing 8 3/8" Sacks cement required 650

Type of Shoe used Teleg. Float collar used None Btm 2 jts welded 7 ft. and back

TD of hole 1357 KB Set 1340 Feet of 8 3/8 Inch 24 # Grade J-55

New-used csg. @ 13-10 with 200 sacks neat cement around shoe (low c 2% cc 14.8
+ 350 sax Flow C additives 6% Gilsonite 1/4" Flocc 2% cc 12.7-13.0

Plug down @ 8:40 (AM) (PM) Date 12-31-73

Cement circulated No No. of Sacks None

Cemented by Denton Witnessed by J. H. W. W. W.

Temp. Survey ran @ 2:30 (AM) (PM) Date 12-31-73 top cement @ 260

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Surface 17 1/2" - 354 KB 9 ft. 13 3/8" 48" H-10

225/sx Class C 4% CC Plug down 8:00 PM 12-28-73

Circulated into cellar and fell back to 60' Filled with

Ready Mix