

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Petr Corp.</i>		Lease <i>J. Long J</i>		Well # <i>6</i>	
Location of Well	Unit <i>1650 2310e</i>	Section <i>22</i>	Township <i>17</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor <i>Cactus Drilling Co.</i>			Type of Equipment <i>Rotary & Start approx 3-19-74</i>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>15"</i>	<i>10 3/4"</i>	<i>32.3</i>	<i>200</i>	<i>200</i>	<i>200 cuic.</i>
<i>9 7/8"</i>	<i>7"</i>	<i>20 + 23</i>		<i>1150</i>	<i>350 "</i>
<i>6 1/4"</i>	<i>4 1/2" + 5 1/2"</i>	<i>9.5 + 15.5</i>		<i>1500</i>	<i>100</i>

Casing Data:

Int
~~Surface~~ *31* joints of *7"* inch *23, 26 #* Grade *J-55* (used)
(Approved) (~~Rejected~~)

Inspected by *L. A. Williams* date _____

Cementing Program

Size of hole *9 7/8* Size of Casing *7"* Sacks cement required *425/*

Type of Shoe used *Texas Am* Float collar used *N/S* Btm *3* jts ~~welded~~ *Thread Lock*

TD of hole *1140 TD* Set *1128 GL* Feet of *7* Inch *23, 26 #* Grade *J-55*

New-used csg. @ *1128 GL* with *125* sacks neat cement around shoe *Class C 2% CC 15.2 15.5*

+ *300* sax *Class C* additives *6% Gilsonite 1/4" Flocl- 2% CC 13.0, 13.5*

Plug down @ *1125* (~~AM~~) (PM) Date *3-23-74*

Cement circulated *1 x 5* No. of Sacks *75/5x*

Cemented by *Benton* Witnessed by *L. A. Williams*

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: *Spud 3-21-74 14 3/4" hole TD 297 7 1/2 10 1/4" 32"*

J-55 New Csg. Set 297 GL 175/5x Class C 4% CC Cuic 20/5x

PD - 9:20

Top SA 721