

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Petr. Corp.</i>		Lease <i>f Jazy f</i>		Well # <i>10</i>	
Location of Well	Unit <i>1750N H 4302</i>	Section <i>22</i>	Township <i>17</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor <i>Cactus & Co.</i>			Type of Equipment <i>Rotary</i>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>14 3/4"</i>	<i>10 3/4"</i>	<i>32</i>		<i>300</i>	<i>175 Cms.</i>
<i>9 7/8"</i>	<i>7"</i>	<i>23+26</i>		<i>1160</i>	<i>400 "</i>
<i>6 1/4</i>	<i>4 1/2 + 5 1/2</i>	<i>9.5 + 15.5</i>		<i>1500</i>	<i>125</i>

Casing Data:

Int.
~~Surface~~ *39* joints of *7"* inch *23* # Grade *Used*
(Approved) (~~Rejected~~)

Inspected by *S. A. Mernis* date _____

Cementing Program

Size of hole *9 7/8* Size of Casing *7* Sacks cement required *500*

Type of Shoe used *None* Float collar used *None* Btm 2 jts ~~welded~~ *Thread Lock*

TD of hole *1205K6* Set *11972* Feet of *7* Inch *23* # Grade *J-55*

New-used csg. @ *1197* with *150* sacks neat cement around shoe *Class C 2% cc* *15.0"*
+ *350* sax *Class C* additives *6% Wilsonite* *6% Flocc* *2% cc* *13.0"*

Plug down @ *8:30* (AM) (PM) Date *8-2-74*

Cement circulated *No* No. of Sacks *None*

Cemented by *Denton* Witnessed by _____

Temp. Survey ran @ *2:45* (AM) (PM) Date *8-3-74* top cement @ *850*

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: *Surface 10ft 10 3/4" TD 323 Set 3232L Ant 175/5x*

Class C 4% cc PD 1:30 AM 7-31-74 Cms 5/5x

1" to 440 Ant 100/5x Class C 4% cc 1" to 300' Ant

125/5x Class C 4% cc PD 10:00 PM Cms 5/5x