

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Marbab Energy Corp</u>		Lease <u>M.G. Phillips State</u>		Well # <u>16</u>	
Location of Well	Unit <u>F</u>	Section <u>27</u>	Township <u>17</u>	Range <u>25</u>	County <u>Edoly</u>
Drilling Contractor <u>Jenkins Dr. Drilling Co.</u>			Type of Equipment <u>CT</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>10"</u>					
<u>8"</u>	<u>7"</u>			<u>500</u>	<u>Pulled</u>
<u>6"</u>	<u>4 1/2"</u>	<u>10 #</u>	<u>New</u>	<u>850</u>	<u>Circ</u>

Casing Data:

Surface 27 joints of 4 1/2" inch 10 # Grade API New K-55
(Approved) (~~Rejected~~)

Inspected by Solan G. Morris date 10-17-75

Cementing Program

Size of hole 10" 6 225, 8" 6 275, 6" 350 Size of Casing 4 1/2 Sacks cement required 130

Type of Shoe used Guide Float collar used 2 1/2 Btm 2 jts welded Thread Lock

TD of hole 850 Set 850 Feet of 4 1/2 Inch 10 # Grade K-55

New-used csg. @ 850 with 50 sacks neat cement around shoe Class C 50-50 14.6 #
+ 100 / sax None Lite additives 12.7 #

Plug down @ 4:00 (~~PM~~) Date 10-17-75

Cement circulated NO No. of Sacks None

Cemented by N. H. Bacter Witnessed by Solan G. Morris

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Circ contaminated cut and mixed for about 3 hrs.
fell back app. 10' and held.