

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Jates Petro Corp.</u>		Lease <u>Ingram Jackson BV</u>			Well # <u>6</u>
Location of Well	Unit <u>D</u> <u>330.N+W</u>	Section <u>26</u>	Township <u>17</u>	Range <u>2-5</u>	County <u>Eddy</u>
Drilling Contractor	<u>Byrd Drilling Co.</u>			Type of Equipment	

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>15"</u>	<u>10 3/4"</u>	<u>32</u>		<u>200</u>	<u>Cin.</u>
<u>9 7/8"</u>	<u>7"</u>	<u>20</u>		<u>1140</u>	<u>"</u>
<u>6 1/4"</u>	<u>4 1/2 + 5 1/2"</u>	<u>10.5 + 13.5</u>		<u>1500</u>	<u>150</u>

Casing Data:

Int:
~~Surface~~ 36 joints of 7 inch 23 # Grade Used API N-80
(Approved) (~~Rejected~~)

Inspected by Lelan Mermin date 8-30-76

Cementing Program

Size of hole 9 7/8" Size of Casing 7" Sacks cement required 500/5X

Type of Shoe used Notched Float collar used None Btm 2 jts ~~welded~~ Thread Lock

TD of hole 1163'KB Set 1150'GL Feet of 7" Inch 23 # Grade N80

New-used csg. @ 1150'GL with 150 sacks neat cement around shoe Class C 2%cc
+ 350 sax Class C Mix additives 5# Gilsonite 4# Facel 2%cc

Plug down @ 3:40 (AM) (PM) Date 8-30-76

Cement circulated Yes No. of Sacks 20

Cemented by Denton Witnessed by Lelan Mermin

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Surface: 14 3/4" Ran 8jts 10 3/4" 40# used

TD 252'KB Int 200/5X Class C 4%cc PD 10:00 AM

8-28-76 Cin 15/5X

Water 290-530, 541-68, 600-29, 925-86, 1043-61