

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Harrington Transportation Inc.</i>		Lease <i>Martin Com.</i>		Well # <i>1</i>	
Location of Well	Unit <i>19805 660W</i>	Section <i>29</i>	Township <i>17</i>	Range <i>26</i>	County <i>Eddy</i>
Drilling Contractor <i>R K A</i>	Type of Equipment <i>Rotary to start approx. 2-11-77</i>				

APPROVED CASING PROGRAM

* *Witness*

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2</i>	<i>13 7/8"</i>	<i>48</i>		<i>350</i>	<i>375 cu</i>
<i>12 1/4</i>	<i>8 7/8"</i>	<i>24</i>		<i>1350</i>	<i>660 cu.</i>
<i>7 7/8"</i>	<i>4 1/2"</i>	<i>11.6</i>		<i>8500</i>	<i>330</i>

Casing Data:

Surface *46* joints of *1 1/2* inch *4* # Grade *55*
(Approved) (Rejected)

Inspected by *(RJ)* date *2-16-77*

Cementing Program

Size of hole *17 1/2* Size of Casing *9 5/8* Sacks cement required *1200*

Type of Shoe used *Half 6 in.* Float collar used ☒ Btm 3 jts welded ☒

TD of hole *1376* Set Feet of *9 7/8* Inch *24* # Grade *55*

New-used csg. @ *1376* with *200* sacks neat cement around shoe

+ *200* sack *Thick Gel 10# 3/4" additives* + *500* sack *1/2" 5# Gilsinite - 1/4" loss - 2700 - first 3/4" lost*

Plug down @ *9:30* (AM) (PM) Date *2-16-77*

Cement circulated *Yes* No. of Sacks *25*

Cemented by *Harrington* Witnessed by *W. H. H.*

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: *Sus Pipe 13 3/8 @ 349' w/400 SY Class C - Circ 200 SY to 54*

404-15, 562-625, 659-668, 670-807, 772-1158