

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Mesa Pet. Co.</u>		Lease <u>Potter Com</u>		Well # <u>1</u>	
Location of Well	Unit <u>B</u> <u>660 N</u> <u>1985 C</u>	Section <u>29</u>	Township <u>17</u>	Range <u>27</u>	County <u>Eddy</u>
Drilling Contractor	<u>Warton Oil Co.</u>		Type of Equipment <u>Rotary to start approx 5-21-77</u>		

* APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 7/8</u>	<u>48</u>		<u>300</u>	<u>350 lbs</u>
<u>11</u>	<u>8 7/8</u>	<u>24</u>		<u>1700</u>	<u>800</u>
<u>7 7/8</u>	<u>4 1/2</u>	<u>10.5 + 11.6</u>		<u>9800</u>	<u>600</u>

Casing Data:

Surface 43 joints of 8 7/8 inch 24 # Grade API New K-55 STD
(Approved) (Rejected)

Inspected by Lelan McManis date 6-6-77

Cementing Program

Size of hole 11 Size of Casing 8 7/8 Sacks cement required 500/sy

Type of Shoe used Guide Float collar used Yes Btm 2 jts welded Threaded

ID of hole 1694 K/S Set 1677 Feet of 8 7/8 Inch 24 # Grade K-55

New-used csg. @ 1677 with 100/sy sacks neat cement around shoe Class C 2800

+ 400 / sax Class C Low Density additives 10 Salt 1/4" Cellulose 5" Silicate 2800

Plug down @ 12:35 (AM) (PM) Date 6-10-77

Cement circulated No No. of Sacks None

Cemented by BS Witnessed by Lelan McManis

Temp. Survey ran @ 7:00 (AM) (PM) Date 6-10-77 top cement @ 150

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Ran 1" to 160' cut 65/sy Class C Neat PD 9:10 AM Line 10/sy
Passible water 405-725, 735-1220, 1309-60