

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Cotton & Cotton</i>		Lease <i>10-19 #1</i>		Well # <i>1</i>	
Location of Well	Unit <i>M</i>	Section <i>23</i>	Township <i>10S</i>	Range <i>38E</i>	County <i>El Paso</i>
Drilling Contractor <i>Hughes Drilling</i>	Type of Equipment <i>Cable Tool</i>				
APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>10"</i>	<i>8 5/8"</i>	<i>24#</i>	<i>90'</i>	<i>90'</i>	
<i>8"</i>	<i>7"</i>	<i>20#</i>		<i>450'</i>	<i>Water shut off</i>
<i>6 3/4"</i>	<i>5 1/2"</i>	<i>14#</i>		<i>845'</i>	
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole _____ Size of Casing <i>5 1/2"</i> Sacks cement required <i>200</i> .					
Type of Shoe used <i>float</i> Float collar used _____ Btm 3 jts welded <i>No</i>					
TD of hole <i>807'</i> Set <i>807'</i> Feet of <i>5 1/2</i> Inch <i>14</i> # Grade <i>J-55</i>					
New-used csg. @ <i>807'</i> with <i>200</i> sacks neat cement around shoe					
+ _____ sax _____ additives <i>170 salt</i>					
Plug down @ <i>11:00</i> (AM) (PM) Date <i>1-20-78</i>					
Cement circulated <i>No</i> No. of Sacks _____					
Cemented by <i>George Denton</i> Witnessed by <i>Mike Stubblefield</i>					
Temp. Survey ran @ <i>1:30</i> (AM) (PM) Date <i>1-20-78</i> top cement @ <i>75'</i>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used <i>wireline</i> Witnessed by <i>M. S.</i>					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <i>will ready mix to top</i>					

12" down to 95'

8" 95' to 350'

6" 350 to 807'