

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Let Corp.</u>		Lease <u>Blowing Rock Com.</u>		Well # <u>1</u>	
Location of Well	Unit <u>960^N 690^W</u>	Section <u>32</u>	Township <u>17</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor <u>Tronaco</u>			Type of Equipment <u>Rotary & start approx. 9-8-77</u>		

APPROVED CASING PROGRAM

* Witness

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2</u>	<u>13 3/8"</u>	<u>48</u>		<u>360+</u>	<u>275 Circulate</u>
* <u>12 1/4 - 11</u>	<u>8 5/8"</u>	<u>24</u>		<u>1400</u>	<u>550 "</u>
<u>7 7/8"</u>	<u>4 1/2 or 5 1/2"</u>			<u>9000</u>	

Casing Data:

Surface 33 joints of 8 5/8 inch 24 # Grade J-55

✓ (Approved) (Rejected)

Inspected by mw date 9/17/77

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 655 SX

Type of Shoe used Guide Float collar used Insert Btm 3 jts welded Yes

TD of hole 1480 Set 1517 Feet of 8 5/8 Inch 24 # Grade J-55

New/used csg. @ 1480 with 200 sacks neat cement around shoe 4 1/2 % CC
+ 455 sax 50/50 Poz additives 2 % CC

Plug down @ 2:50 (AM) (PM) Date 9/17/77

Cement circulated Yes No. of Sacks 15

Cemented by Dowell Witnessed by mw

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witessed by

Checked for shut off @ (AM) (PM) Date

Method used Witessed by

Remarks: Surface - 495' - 54# - 13 3/8" - Cemented w/ 380 SX Class C w/ 4% CC - Circ. 30 SXS

Centralizer 46' from btm - Centralizers + baskets 940' from btm + 495' from surface

Last bucket 13.02'