

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Mesa Lata Co.</i>		Lease <i>Bogle State Com.</i>		Well # <i>1</i>	
Location of Well	Unit <i>2560N 660E</i>	Section <i>2</i>	Township <i>16</i>	Range <i>27</i>	County <i>Eddy</i>
Drilling Contractor <i>Warton Drilling Co.</i>			Type of Equipment <i>Rotary & start approx 10-5-77</i>		

APPROVED CASING PROGRAM

* *Witness*

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2"</i>	<i>13 3/8"</i>	<i>48</i>		<i>350</i>	<i>400 circ.</i>
<i>11"</i>	<i>8 5/8"</i>	<i>24</i>		<i>1800</i>	<i>800 "</i>
<i>7 1/8"</i>	<i>4 1/2"</i>	<i>11.6</i>		<i>9000</i>	

Casing Data:

Surface *40* joints of *8 5/8* inch *24* # Grade *API New K-55*

(Approved) (Rejected)

Inspected by *Lelan Mermin* date *10-26-77*

Cementing Program

Size of hole *11"* Size of Casing *8 5/8"* Sacks cement required *675/sk*

Type of Shoe used *Guide* Float collar used *Insert Btm 2 jts* ~~welded~~ *Thread-Loek*

TD of hole *1632'K* Set *1617'6"* Feet of *8 5/8* inch *24* # Grade *K-55*

New-used csg. @ *1617'6"* with *200* sacks neat cement around shoe *Class C 2%cc*
+ *475/sax* *Huaco Lite* additives *5 #* *Gilsonite* *1/4 #* *Flocc* *2/10cc*

Plug down @ *7:30 (AM)* ~~(PM)~~ Date *10-26-77*

Cement circulated *No* No. of Sacks *None*

Cemented by *Halliburton* Witnessed by *Lelan Mermin*

Temp. Survey ran @ *2:00 (AM)* ~~(PM)~~ Date *10-26-77* top cement @ *1:30 -*

Casing test @ *(AM)* ~~(PM)~~ Date

Method Used *(AM)* ~~(PM)~~ Witnessed by

Checked for shut off @ *(AM)* ~~(PM)~~ Date

Method used *(AM)* ~~(PM)~~ Witnessed by

Remarks: *Set slips:*

No water brakes according to samples. Brakes are potash salt

258-1251, 1314-25