

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Yates Petr. Corp.</i>		Lease <i>Yates KA Com.</i>		Well # <i>1</i>	
Location of Well	Unit <i>6605 1980w</i>	Section <i>24</i>	Township <i>17</i>	Range <i>24</i>	County <i>Eddy</i>
Drilling Contractor	<i>Cupatum # 4</i>		Type of Equipment <i>Rotary to start 10-16-78</i>		
APPROVED CASING PROGRAM					
<i>* witness</i>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>17 1/2</i>	<i>13 3/8</i>	<i>48</i>		<i>280</i>	<i>150 circ.</i>
<i>12 1/4</i>	<i>8 7/8</i>	<i>24</i>		<i>950</i>	<i>500 "</i>
<i>7 7/8</i>	<i>4 1/2 or 5 1/2</i>			<i>8200</i>	
Casing Data:					
<i>Inter</i> Surface joints of <i>8 5/8</i> inch <i>24</i> # Grade <i>K-55</i>					
(Approved) (Rejected)					
Inspected by _____ date _____					
Cementing Program					
Size of hole <i>12 1/4</i> Size of Casing <i>8 5/8</i> Sacks cement required <i>700</i> sx					
Type of Shoe used <i>guide</i> Float collar used <i>insert</i> Btm 3 jts welded <i>yes</i>					
TD of hole <i>960'</i> Set <i>960'</i> Feet of <i>8 5/8</i> Inch <i>24</i> # Grade <i>K-55</i>					
New-used csg. @ <i>960'</i> with <i>150</i> sacks neat cement around shoe + <i>200</i> sax <i>thin set</i> additives <i>10" gilsonite - 1/2" # 40</i>					
Plug down @ <i>5:30</i> (AM) (PM) Date <i>10/23/78</i>					
Cement circulated <i>No</i> No. of Sacks _____					
Cemented by <i>Hallidorton</i> Witnessed by <i>Mike Stutfield</i>					
Temp. Survey ran @ <i>12:00</i> (AM) (PM) Date <i>10/24/78</i> top cement @ <i>320'</i>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <i>2 baskets @ 640' + 500' 3 centralizers @ 920' - 640' - 500'</i>					
<i>Last bkg. break @ 840'</i>					
<i>+350 sx Hall. Lte 5# gilsonite - 1/4" # 40 - 270 cc last circ. @ 664</i>					

Last bkg. break @ 840'

1st Tagged. TOC @ 320'

Circ. was again