

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>J & L Enterprises</u>		Lease <u>Gulf Times</u>		Well # <u>3</u>	
Location of Well	Unit <u>P</u> <u>330S</u> <u>330E</u>	Section <u>22</u>	Township <u>17</u>	Range <u>28</u>	County <u>Eddy</u>
Drilling Contractor <u>Artesia Fishing tool</u>		Type of Equipment <u>Rotary to start 10-10-79</u>			
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>7 7/8"</u>	<u>5 1/2"</u>	<u>14</u>		<u>800</u>	<u>250 cwt.</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>7 7/8</u> Size of Casing <u>5 1/2</u> Sacks cement required _____					
Type of Shoe used <u>848</u> Float collar used <u>Float</u> ^{Shoe} Btm 3 jts welded <u>yes</u>					
TD of hole <u>848</u> Set <u>850</u> Feet of <u>5 1/2</u> Inch <u>14</u> # Grade <u>J-40</u>					
New-used csg. @ <u>850</u> with <u>150</u> sacks neat cement around shoe					
+ _____ sax _____ additives <u>2% CC</u>					
Plug down @ <u>1130</u> (AM) (PM) Date <u>10-13-79</u>					
Cement circulated <u>NO</u> No. of Sacks _____					
Cemented by <u>Hewco</u> Witnessed by <u>BW Weaver</u>					
Temp. Survey ran @ <u>8:00</u> (AM) (PM) Date <u>10-14-79</u> top cement @ <u>125</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>4 Centerligers on Bottom 4 Joints</u>					
Ready-mixed well to surface 4 yds. M.S.					