

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Corp.</u>		Lease <u>East Roper LP Com.</u>		Well # <u>1</u>																									
Location of Well	Unit <u>11305</u> <u>1300 C</u>	Section <u>30</u>	Township <u>17</u>	Range <u>26</u>	County <u>Eddy</u>																								
Drilling Contractor	<u>Lander Ditz Co</u>		Type of Equipment <u>Rotary</u>																										
<i>* witness</i> <u>APPROVED CASING PROGRAM</u> <table border="1"> <thead> <tr> <th>Size of Hole</th> <th>Size of Casing</th> <th>Weight Per Foot</th> <th>New or Used</th> <th>Depth</th> <th>Sacks Cement</th> </tr> </thead> <tbody> <tr> <td><u>17 1/2"</u></td> <td><u>13 7/8"</u></td> <td><u>28</u></td> <td></td> <td><u>400</u></td> <td><u>250 c.</u></td> </tr> <tr> <td><u>12 1/4"</u></td> <td><u>8 5/8"</u></td> <td><u>24</u></td> <td></td> <td><u>1300</u></td> <td><u>600 "</u></td> </tr> <tr> <td><u>7 7/8"</u></td> <td><u>4 1/2" or 5 1/2"</u></td> <td></td> <td></td> <td><u>8600</u></td> <td><u>250</u></td> </tr> </tbody> </table>						Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement	<u>17 1/2"</u>	<u>13 7/8"</u>	<u>28</u>		<u>400</u>	<u>250 c.</u>	<u>12 1/4"</u>	<u>8 5/8"</u>	<u>24</u>		<u>1300</u>	<u>600 "</u>	<u>7 7/8"</u>	<u>4 1/2" or 5 1/2"</u>			<u>8600</u>	<u>250</u>
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement																								
<u>17 1/2"</u>	<u>13 7/8"</u>	<u>28</u>		<u>400</u>	<u>250 c.</u>																								
<u>12 1/4"</u>	<u>8 5/8"</u>	<u>24</u>		<u>1300</u>	<u>600 "</u>																								
<u>7 7/8"</u>	<u>4 1/2" or 5 1/2"</u>			<u>8600</u>	<u>250</u>																								
Casing Data:																													
Surface <u> </u> joints of <u>8 5/8</u> inch <u>24</u> # Grade <u>J-55</u>																													
<u>Yes</u> (Approved) (Rejected)																													
Inspected by <u>B.W. Weaver</u> date <u>2-10-80</u>																													
Cementing Program																													
Size of hole <u>12 1/4</u> Size of Casing <u>8 5/8</u> Sacks cement required <u>150 C</u>																													
Type of Shoe used <u>Guide</u> Float collar used <u>Insert</u> Btm 3 jts welded <u>yes</u>																													
TD of hole <u>1245</u> Set <u>1248</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>J-55</u>																													
New used csg. @ <u>1248</u> with <u>150</u> sacks neat cement around shoe																													
+ <u>430</u> sax <u>65-35 Pos</u> additives <u>4% Jel 1/4 Flo Seal #5 Gilsomite 2% Calum chloride</u>																													
Plug down @ <u>3:40</u> (PM) (PM) Date <u>2-10-80</u>																													
Cement circulated <u>NO</u> No. of Sacks <u>NONE</u>																													
Cemented by <u>Dewell</u> Witnessed by <u>B.W. Weaver</u>																													
Temp. Survey ran @ <u>9:30</u> (PM) (PM) Date <u>2-10-80</u> top cement @ <u>520</u>																													
Casing test @ <u> </u> (AM) (PM) Date <u> </u>																													
Method Used <u> </u> Witnessed by <u> </u>																													
Checked for shut off @ <u> </u> (AM) (PM) Date <u> </u>																													
Method used <u> </u> Witnessed by <u> </u>																													
Remarks: <u>Loss Circulation Zone @ 1136</u>																													

Ran 1" to 520 ft mixed 66 SX class C 4% Calum Chloride
Ran 1" to 260 ft mixed 106 SX class C 4% Calum Chloride
And Circulated Cement 2-10-80 By BWW