

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Collier Energy Inc.</u>		Lease <u>State B 11112.1</u>		Well # <u>8</u>	
Location of Well	Unit H <u>2310 FNL</u> <u>330 FEL</u>	Section <u>22</u>	Township <u>17</u>	Range <u>28</u>	County <u>Cddy</u>
Drilling Contractor	<u>Yucca Dry Co.</u>		Type of Equipment <u>Rotary</u>		
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>7 7/8</u>	<u>4 1/2"</u>	<u>9.5</u>		<u>800'</u>	<u>250</u>
<u>8 1/4</u>	<u>8 3/8</u>	<u>PBC 160</u>		<u>60'</u>	<u>Ready-mixed</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____ (Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>7 7/8"</u> Size of Casing <u>4 1/2"</u> Sacks cement required _____					
Type of Shoe used <u>guide</u> Float collar used <u>yes</u> Btm 3 jts welded <u>No</u>					
TD of hole <u>855'</u> Set <u>850'</u> Feet of <u>4 1/2</u> Inch <u>9.5</u> # Grade <u>J-55</u>					
<u>New</u> -used csg. @ <u>850'</u> with <u>100%</u> <u>sop</u> sacks neat cement around shoe + <u>150</u> sax <u>Hall's Oite</u> additives <u>6# salt, 6# gelsomite, 1/4# flozele</u>					
Plug down @ <u>4:35</u> (AM) (PM) Date <u>3/28/80</u>					
Cement circulated <u>No</u> No. of Sacks <u>-0-</u>					
Cemented by <u>Halliburton</u> Witnessed by <u>Mike Stillefeld</u>					
Temp. Survey ran @ <u>8:00</u> (AM) (PM) Date <u>3/29/80</u> top cement @ <u>30'</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>50% sop, (6# salt, 39% CFR², 29% gel)</u>					
<u>Ready mix with 2 yd 4-1-80 By BWW</u>					
<u>centralizers @ 830'-790'</u> <u>Wtr @ 118'-333'</u> (Fresh) (Salt)					