

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 100
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

| | | | | | |
|---|------------------|----------------------|------------------------------------|--------------------|-----------------------|
| Operator <u>Marathon Energy Corp</u> | | Lease <u>Abo</u> | | Well # <u>4</u> | |
| Location of Well <u>605 223</u> | Unit <u>N</u> | Section <u>27</u> | Township <u>17</u> | Range <u>28</u> | County <u>Eddy</u> |
| Drilling Contractor <u>Yucca</u> | | | Type of Equipment <u>Rotary</u> | | |

* witness

APPROVED CASING PROGRAM

| Size of Hole | Size of Casing | Weight Per Foot | New or Used | Depth | Sacks Cement |
|--------------|----------------|-----------------|-------------|-------|--------------|
| 11 | 8 5/8 | 24 # | | 80 | Ready-mix |
| 7 7/8 | 4 1/2 | 10.5 | | 1000 | 250 SX Circ |
| | | | | | |

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected) _____

Inspected by _____ date _____

Cementing Program

Size of hole 7 7/8" Size of Casing 4 1/2" Sacks cement required _____

Type of Shoe used guide Float collar used insert Btm 2 jts welded yes

TD of hole 1020' Set 1020' Feet of 4 1/2 Inch 10.5 # Grade J-SS

New-used csg. @ 1020' with 100sxH sacks neat cement around shoe
+ 150 sax Hall, Lite additives 5# gilsonite, 1/4# florel, 6# salt, 5% cfr2

Plug down @ 3845 (AM) (PM) Date 6/25/80

Cement circulated yes No. of Sacks 15

Cemented by Halliburton Witnessed by Mike Stubblefield

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: _____

centralizers @ 990'-930'-870'-810'-750' No water