

File 103  
updating File

CO. OIL CONSERVATION ASSOCIATION  
DRAWER 10  
ARTESIA, NEW MEXICO

REPORT FOR CEMENTING OF WELLS

Operator <u>Celeste C Grynberg</u>		Lease <u>South Cottonwood Draw</u>		Well # <u>1</u>	
Location of Well	Unit <u>660S 1980w N</u>	Section <u>29</u>	Township <u>16</u>	Range <u>24</u>	County <u>Eddy</u>
Drilling Contractor	?		Type of Equipment <u>Rotary</u> <u>Feb-20, 1981</u>		

\* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
24"	20"			40'	
16"	13 3/8"	48#		160'	Circ
12 1/4"	8 5/8"	28#		1000'	Circ
7 7/8"	4 1/2"	10.5#		7000'	-

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
(Approved) (Rejected) \_\_\_\_\_

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required \_\_\_\_\_

Type of Shoe used Tex-Pat Float collar used Float Collar Btm 3 jts welded yes

TD of hole 930 Set 940 Feet of 8 5/8 Inch 28 # Grade J-55

New-used csg. @ 940 with 250 sacks neat cement around shoe  
+ 300 sax Hewco Lite additives 11-20-81

Plug down @ 6.00 (~~PM~~) (PM) Date \_\_\_\_\_

Cement circulated Did Not Circulate No. of Sacks \_\_\_\_\_

Cemented by Hewco Witnessed by BW Weaver

Temp. Survey ran @ 11:00 (~~AM~~) (PM) Date 11-20-81 top cement @ 180

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: Loss Zone @ 578 and 712

150  
Ran 1" and mixed SX Class C 3% CC Tagged @ 147 ft

Ran 200 SX Class C and Circulated Cement