

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>KPM Energy Inc</u>		Lease <u>Exxon A</u>		Well # <u>2</u>	
Location of Well	Unit <u>23105 2310E J</u>	Section <u>21</u>	Township <u>16</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor	<u>S+B Drlg</u>		Type of Equipment <u>Rotary 10-20-81</u>		

\*witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>9 7/8</u>	<u>7"</u>	<u>17#</u>		<u>1050'</u>	<u>360 SX Circ</u>
<u>6 1/8</u>	<u>4 1/4</u>	<u>9.5#</u>		<u>1450</u>	<u>160 SX</u>

Casing Data:

Surface \_\_\_\_\_ joints of 7 inch 17 # Grade K55

B.W. Weaver (Approved) (Rejected)

Inspected by B.W. Weaver date \_\_\_\_\_

Cementing Program

Size of hole 9 7/8 Size of Casing 7 Sacks cement required 400

Type of Shoe used Tex Pat Float collar used Insert Btm 3 jts welded yes

TD of hole 1140 Set 1150 Feet of 7 Inch 17 # Grade K-55

New-~~rod~~ csg. @ 1150 with 400 sacks neat cement around shoe

+ \_\_\_\_\_ sax \_\_\_\_\_ additives \_\_\_\_\_

Plug down @ 2:00 (~~PM~~) (PM) Date 11-11-81

Cement circulated yes No. of Sacks 600

Cemented by Hawco Witnessed by B.W. Weaver

Temp. Survey ran @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_ top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: \_\_\_\_\_