

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Gates Petr. Corp.</i>		Lease <i>Ingram Jackson "BV"</i>		Well # <i>8</i>	
Location of Well	Unit <i>B</i>	Section <i>27</i>	Township <i>17</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor	<i>L + M #2</i>		Type of Equipment <i>Rotary</i>		

* Witness 7"

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>14 1/2 "</i>	<i>10 3/4 "</i>	<i>30 #</i>		<i>350'</i> <i>340'</i>	<i>200 Sx</i>
* <i>9 1/2 "</i>	<i>7 "</i>	<i>23 #</i>		<i>1140</i>	<i>400 Sx</i>
<i>6 1/2 "</i>	<i>4 1/2 "</i>	<i>9.5 #</i>		<i>1500</i>	<i>125 Sx</i>

Casing Data:

Surface _____ joints of _____ inch _____ # Grade _____
(Approved) (Rejected)

Inspected by _____ date _____

Cementing Program

Size of hole *9 1/4 "* Size of Casing *10 "* Sacks cement required _____

Type of Shoe used *guide* Float collar used *1200 lb* Btm 3 jts welded *yes*

TD of hole *1137'* Set *1139'* Feet of *10 "* Inch *20 #* Grade *J-55*

New-used csg. @ *1137'* with *200 2 1/2* sacks neat cement around shoe
+ *175* sack *Paracetic Lite* additives (*10% glycol, 1/2% colloid, 3% oil*)

Plug down @ *1135-5* (AM) (PM) Date *9/4/52*

Cement circulated *No* No. of Sacks *0*

Cemented by *W. J. Jones Co.* Witnessed by *W. J. Jones*

Temp. Survey ran @ *7300* (AM) (PM) Date *9/4/52* top cement @ *240'*

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks:

with 80% volume of TD

inst. only down to 800'

1. Ran 1" tbg + tripped to c 250'
Pumped 14556 C
cement circulated to surface.