

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DP  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <b>Yates Pet. Co.</b>		Lease <b>Mitchell IN</b>		Well # <b>4</b>	
Location of Well	Unit <b>I</b>	Section <b>23</b>	Township <b>17S</b>	Range <b>25E</b>	County <b>Eddy</b>
Drilling Contractor	<b>L/M #2</b>		Type of Equipment <b>Rotary</b>		
*Witness					
APPROVED CASING PROGRAM					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<b>14 1/2"</b>	<b>10 3/4"</b>	<b>30#</b>	<b>New</b>	<b>350'</b>	<b>Circ</b>
<b>9 1/2"</b>	<b>7"</b>	<b>23#</b>	<b>"</b>	<b>1150'</b>	<b>Circ</b>
<b>6 1/2"</b>	<b>4 1/2"</b>	<b>9.5#</b>	<b>"</b>	<b>1500'</b>	<b>Circ</b>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>9 1/2</u> Size of Casing <u>7</u> Sacks cement required _____					
Type of Shoe used <u>Tex-Pet</u> Float collar used <u>Insert</u> Btm 3 jts welded <u>Yes</u>					
TD of hole <u>1155</u> Set <u>1159</u> Feet of <u>7</u> Inch <u>23</u> # Grade <u>J-55</u>					
New-used csg. @ <u>1159</u> with <u>150</u> sacks neat cement around shoe					
+ <u>300 sk</u> sax <u>Hewco lite</u> additives _____					
Plug down @ <u>1030</u> ( <del>AM</del> ) (PM) Date <u>11-12-82</u>					
Cement circulated <u>NO</u> No. of Sacks _____					
Cemented by <u>Hewco</u> Witnessed by <u>BW Weaver</u>					
Temp. Survey ran @ <u>4:30</u> (AM) ( <del>PM</del> ) Date <u>11-13-82</u> top cement @ <u>500</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>Loss Fluid @ 755</u>					

Ran 1" to 512 ft Cement 50 sk C 3% CC  
 Tag @ 400 ft Cement 50 sk C 3%  
 Tag @ 416 Cement 35 sk C 3%  
 Tag @ 362 Cement 85 sk C 3% Air Cement to surface