

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER ED  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet Corp.</u>		Lease <u>Eagle Creek BL</u>		Well # <u>4</u>	
Location of Well	Unit <u>N</u>	Section <u>23</u>	Township <u>17</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>L/M 2</u>		Type of Equipment <u>Rotary</u>		

\* WITNESS APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 1/2"</u>	<u>10 3/4"</u>	<u>32 #</u>	<u>NEW</u>	<u>350</u>	<u>CIRC</u>
* <u>9 1/2"</u>	<u>7"</u>	<u>23 #</u>	<u>"</u>	<u>1150</u>	<u>CIRC</u>
<u>6 1/4"</u>	<u>4 1/2"</u>	<u>9.5 #</u>	<u>"</u>	<u>TD</u>	<u>CIRC</u>

Casing Data:

Surface            joints of            inch            # Grade             
(Approved) (Rejected)           

Inspected by            date           

Cementing Program

Size of hole 9 7/8" Size of Casing 7" Sacks cement required           

Type of Shoe used guide Float collar used insert Btm 3 jts welded yes

TD of hole 1140' Set 1140' Feet of 7" Inch 23 # Grade J-55

(New-used csg. @ 1140' with 150 2%cc sacks neat cement around shoe  
+ 325 sax Paceretter Lite additives (14 # floreal, 10 # gilsonite, 3 %cc)

Plug down @ 1130 (AM) (PM) Date 3/5/83

Cement circulated Yes No. of Sacks 355x

Cemented by Western Co. Witnessed by Mike Stubblefield

Temp. Survey ran @            (AM) (PM) Date            top cement @           

Casing test @            (AM) (PM) Date           

Method Used            Witnessed by           

Checked for shut off @            (AM) (PM) Date           

Method used            Witnessed by           

Remarks:           

           Lost circ. @ 835' + regained @ 997'.

No centralizers or baskets Lost drill break @ 1050'