

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet Inc.</u>		Lease <u>Gissler AV</u>		Well # <u>37</u>	
Location of Well	Unit <u>K</u>	Section <u>23</u>	Township <u>17</u>	Range <u>25</u>	County <u>EDDY</u>
Drilling Contractor	<u>LARUE #2</u>		Type of Equipment <u>ROTARY</u>		
* Witness <u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 3/4"</u>	<u>10 3/4"</u>	<u>32#</u>	<u>NEW</u>	<u>320'</u>	<u>CIRC</u>
* <u>9 1/2"</u>	<u>7"</u>	<u>23#</u>	<u>"</u>	<u>1150'</u>	<u>CIRC</u>
<u>6 1/4"</u>	<u>4 1/2"</u>	<u>9.5#</u>	<u>"</u>	<u>TD</u>	<u>CIRC</u>
Casing Data:					
Surface <u>          </u> joints of <u>          </u> inch <u>          </u> # Grade <u>          </u>					
<u>          </u> (Approved) (Rejected)					
Inspected by <u>          </u> date <u>          </u>					
Cementing Program					
Size of hole <u>9 3/4</u> Size of Casing <u>7</u> Sacks cement required <u>150</u>					
Type of Shoe used <u>Jex-Pat</u> Float collar used <u>Insert</u> Btm 3 jts welded <u>yes</u>					
TD of hole <u>1171</u> Set <u>1173</u> Feet of <u>7</u> Inch <u>23</u> # Grade <u>J-55</u>					
New-used csg. @ <u>1173</u> with <u>150</u> sacks neat cement around shoe					
+ <u>150</u> sax <u>Pace Setter</u> additives <u>1/4 Flo Seal #5 Gilsen</u> <u>3% cc</u>					
Plug down @ <u>625</u> ( <del>AM</del> ) (PM) Date <u>9-14-83</u>					
Cement circulated <u>no</u> No. of Sacks <u>          </u>					
Cemented by <u>Western</u> Witnessed by <u>B. W. W. W.</u>					
Temp. Survey ran @ <u>12:30</u> (AM) ( <del>PM</del> ) Date <u>9-15-83</u> top cement @ <u>730</u>					
Casing test @ <u>          </u> (AM) (PM) Date <u>          </u>					
Method Used <u>          </u> Witnessed by <u>          </u>					
Checked for shut off @ <u>          </u> (AM) (PM) Date <u>          </u>					
Method used <u>          </u> Witnessed by <u>          </u>					
Remarks: <u>Loss Circulation @ 730 Last Drilling Break 1060</u>					
<u>Ran 1" to 730 ft Cemented 50 SX Class C 3% CC</u>					

Tag @ 730 50 SX C 3% CC

Tag @ 130 50 SX C 3% CC

Tag @ 622 50 SX C 3% CC

Tag @ 545 50 SX C 3% CC

Tag @ 523 50 SX C 3% CC

Tag @ 499 50 SX C 3% CC

50 SX C 3% CC Circulated to surface @ 4:15 PM