

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Co.</u>		Lease <u>JACKSON AT</u>		Well # <u>18</u>	
Location of Well	Unit <u>0</u>	Section <u>14</u>	Township <u>17</u>	Range <u>25</u>	County <u>EDDY</u>
Drilling Contractor	<u>L/M #2</u>		Type of Equipment <u>ROTARY</u>		
* Witness <u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 1/2"</u>	<u>10 3/4"</u>	<u>32#</u>	<u>NEW</u>	<u>320'</u>	<u>2152</u>
* <u>9 1/2"</u>	<u>7"</u>	<u>23 #</u>	<u>"</u>	<u>1150'</u>	<u>"</u>
<u>6 1/4"</u>	<u>4 1/2"</u>	<u>9.5#</u>	<u>"</u>	<u>TD</u>	<u>"</u>
Casing Data:					
Surface _____ joints of _____ inch _____ # Grade _____					
(Approved) (Rejected) _____					
Inspected by _____ date _____					
Cementing Program					
Size of hole <u>9 3/4</u> Size of Casing <u>7</u> Sacks cement required _____					
Type of Shoe used <u>Tex-Ret</u> Float collar used <u>Insert</u> Btm 3 jts welded <u>Yes</u>					
TD of hole <u>1130</u> Set <u>1132</u> Feet of <u>7</u> Inch <u>20</u> # Grade <u>J-55</u>					
New-used csg. @ <u>1132</u> with <u>200</u> sacks neat cement around shoe					
+ <u>225</u> sax <u>Pace Setter</u> life additives <u>1/4 Fl. Sol.</u> , <u>#5 Gilsomite</u> , <u>3% Calcium Chloride</u>					
Plug down @ <u>230 AM</u> (AM) (PM) Date <u>10-1-83</u>					
Cement circulated <u>NO</u> No. of Sacks _____					
Cemented by <u>Western</u> Witnessed by <u>BW Weave</u>					
Temp. Survey ran @ <u>8:30</u> (AM) (PM) Date <u>10-1-83</u> top cement @ <u>730</u>					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>Loss zone @ 720 Last Drilling Break 1086</u>					
Raw 1" to 520 ft					
505X C 4% CC Tag @ 393					
505X C 4% CC Tag @ 393					
505X C 4% CC Tag @ 375					
--- CVC 4% CC Circulated Cement to surface					