

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Co.</u>		Lease <u>JACKSON ESTATE BY</u>			Well # <u>18</u>
Location of Well	Unit <u>F</u>	Section <u>22</u>	Township <u>17</u>	Range <u>25</u>	County <u>EDDY</u>
Drilling Contractor	<u>LARUE # 2</u>		Type of Equipment <u>ROTARY</u>		

\* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
14 1/2	10 3/4"	32#	NEW	320'	CIRC
* 9 1/2	7"	23#	"	1150'	"
6 1/4	4 1/2"	9.5#	"	TD	"

Casing Data:

Surface 29 joints of 7 inch 23 # Grade J-55

Yes (Approved) (Rejected)

Inspected by B.W. Weaver date 8-29-83

Cementing Program

Size of hole 9 7/8 Size of Casing 7 Sacks cement required 200

Type of Shoe used Tex-Art Float collar used INSERT Btm 3 jts welded Yes

TD of hole 1162 Set 1164 Feet of 7 Inch 23 # Grade J-55

New ~~and~~ csg. @ 1164 with 200 sacks neat cement around shoe

+ 350 sax Pace Setter lite additives #5 Gilsprite 1/4 Flo-Seal 3% CC

Plug down @ 9:30 (AM) (PM) Date 8-29-83

Cement circulated NO No. of Sacks

Cemented by Western Witnessed by B.W. Weaver

Temp. Survey ran @ 4:00 (AM) (PM) Date 8-29-83 top cement @ 325

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Loss Circulation 985 ft

Ran 1" to 341 ft and circulated cement with 90 sx class C