

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet. Co.</u>		Lease <u>Gable FV</u>		Well # <u>2</u>	
Location of Well	Unit <u>G</u>	Section <u>29</u>	Township <u>17</u>	Range <u>25</u>	County <u>Eddy</u>
Drilling Contractor	<u>Larue #2</u>		Type of Equipment <u>Rotary</u>		

**\* Witness** APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 1/2</u>	<u>10 3/4"</u>	<u>30 #</u>	<u>NEW</u>	<u>320'</u>	<u>CIRC.</u>
<u>* 9 1/2</u>	<u>7"</u>	<u>23 #</u>	<u>"</u>	<u>1100'</u>	<u>"</u>
<u>6 1/4</u>	<u>4 1/2"</u>	<u>9.5 #</u>	<u>"</u>	<u>TD</u>	<u>"</u>

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
(Approved) (Rejected)

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 9 1/2 Size of Casing 7 Sacks cement required 200

Type of Shoe used Tex-Rt Float collar used Insert Btm 3 jts welded Yes

TD of hole 1140 Set 1142 Feet of 7 Inch 23 # Grade J-JJ

New-used csg. @ 1142 with 200 sacks neat cement around shoe

+ 225 sax Pace Setter lite additives 1/4 Flo Seal #10 Gilsomite 3% Calcium Chloride

Plug down @ 7:45 (AM) (PM) Date 9-27-83

Cement circulated No No. of Sacks \_\_\_\_\_

Cemented by Western Witnessed by B.W. Weaver

Temp. Survey ran @ 2:00 (AM) (PM) Date 9-27-83 top cement @ \_\_\_\_\_

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: Loss Circulation @ 610

Run 1" to 610 FT 50 SXC 3% CC

Tag 560 50 SXC 3%

Tag 415 50 SXC 3%

Tag 332 100 SXC 3% CC Cure Cement