STATE OF NEW MEXICO  ENERGY AND MINERALS DEPARTMENT  OIL CONSERVATION REPUBLICATION  P. O. BOX 2088  SANTA FE SANTA FE, NEW NEXISO 87581 1983	Form C-103 Revised 10-1-78
U.S.O.S.  LAND OFFICE  OFERATOR  ARTESIA, OFFICE	State State Oil & Gas Lease No.
SUNDRY NOTICES AND REPORTS ON WELLS  (DO NOT USE THIS FORM FOR PROPOSALS TO CRICK ON TO CEIPEN OR PLUG BACK TO A DIFFERENT RESERVOIR.  OIL TO GAB  GAB  OIL TO GAB  OIL TO GAB  SUNDRY NOTICES AND REPORTS ON WELLS  (PCAM C-101) FOR SUCH PROPOSALS.)	7. Unit Agreement Hanse
Name of Operator	8. Farm or Lease Name Gable FV
Yates Petroleum Corporation  Address of Operator	9. Well No.
207 South 4th St., Artesia, NM 88210	2
Location of Well  G 2310 FEET FROM THE NORTH LINE AND 1650 FEET FROM	Eagle Creek SA
East LINE, SECTION 29 TOWNSHIP 178 MANGE 25E NAPM.	
15. Elevation (Show whether DF, RT, GR, etc.)	12. County
Check Appropriate Box To Indicate Nature of Notice, Report or Otl	Eddy ///////
NOTICE OF INTENTION TO:  SUBSEQUENT REPORT OF:	
PERFORM REMEDIAL WORK PLUG AND ABANDON REMEDIAL WORK  COMMENCE DRILLING OPHS.  CHANGE PLANS CASING TEST AND CEMENT JOB  The ownediate Casing	ALTERING CASING PLUG AND ABANDONMENT
OTHER Intermediate Casi	ing X
. Describe Proposed or Completed Operations (Clearly state all pertinent details, and give pertinent dates, including	estimated date of starting any proposed
Ran 28 joints 7" 20# J-55 casing set 1143'. 1-Texas Pattern guide sh float set 1104'. Cemented w/225 sacks Pacesetter Lite, 5#/sack gilso celloseal, 3% CaCl2. Tailed in w/200 sacks Class "C" 2% CaCl2. Com of cement - 1250 psi in 12 hours. PD 7:45 AM 9-27-83. Bumped plug t pressure and float held okay. Cement did not circulate. WOC 6 hours Survey and found top of cement 610'. Ran 1". Tagged cement 610'. S Class "C" 3% CaCl2. PD 2:00 PM 9-27-83. WOC 2 hours. Ran 1". Tagg 50 sacks Class "C" 3% CaCl2. PD 4:30 PM 9-27-83. WOC 2 hours. Ran 415'. Spotted 50 sacks Class "C" 3% CaCl2. PD 6:45 PM 9-27-83. WOC Tagged cement 338'. Spotted 100 sacks Class "C" 3% CaCl2. PD 10:00 circulated 10 sacks to pit. WOC. Drilled out 6:00 AM 9-28-83. WOC Nippled up and tested to 1000# for 30 minutes, okay. Reduced hole to and resumed drilling.	onite, 1/4#/sack repressive strength to 1000 psi, released to. Ran Temperature topotted 50 sacks topotted 50'. Spotted 1". Tagged cement to 2 hours. Ran 1". PM 9-27-83. Cement topotted 50'. Spotted
E. I hereby certify that the information above is true and complete to the best of my knowledge and belief.  THE Production Supervisor	9-28-83
Original Signed By Leslie A. Clement	SEP 2 9 198€

Leslie A. Clements

INDITIONS OF APPROVAL, IF ANY SUPERVISOR DISTRICT IL