

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>YPC</u>		Lease <u>GISSLER AV</u>		Well # <u>43</u>	
Location of Well	Unit <u>F</u>	Section <u>23</u>	Township <u>N</u>	Range <u>25</u>	County <u>EDDY</u>
Drilling Contractor	<u>AFT 1</u>		Type of Equipment <u>ROTARY</u>		

* Witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>14 1/2</u>	<u>10 3/4"</u>	<u>40 #</u>	<u>NEW</u>	<u>320'</u>	<u>CIRC</u>
* <u>9 1/2</u>	<u>7"</u>	<u>23 #</u>	<u>"</u>	<u>1170'</u>	<u>CIRC.</u>
<u>6 1/4</u>	<u>4 1/2"</u>	<u>9.5 #</u>	<u>"</u>	<u>TD</u>	<u>CIRC.</u>

Casing Data:

Surface 29 joints of 7 inch 23 # Grade J-55

Yes

(Approved) (Rejected)

Inspected by BW Weaver date _____

Cementing Program

Size of hole 9 7/8 Size of Casing 7 Sacks cement required _____

Type of Shoe used Tex-Rat Float collar used Insert Btm 3 jts welded yes

TD of hole 1160 Set 1162 Feet of 7 Inch 23 # Grade J-55

New-used csg. @ 1162 with 200 sacks neat cement around shoe

+ 225 sax Pace Setter lite additives 2% CC

Plug down @ 11:00 (AM) (PM) Date 11-23-83

Cement circulated NO No. of Sacks _____

Cemented by Western Witnessed by BW Weaver

Temp. Survey ran @ 5:00 (AM) (PM) Date 11-23-83 top cement @ 740

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Run 1" to 379 505X C 3 1/4 CC

Tag 379 505X C 3 1/2 CC, Tag @ 379 Pmpd. 50 Sxs Cl. C 3 1/2 CC

Tag 205 505X C 3 1/2 Complete Cement