

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <b>RPM Energy Inc</b>		Lease <b>State</b>		Well # <b>3</b>	
Location of Well	Unit <b>330N 330W D</b>	Section <b>16</b>	Township <b>16</b>	Range <b>26</b>	County <b>Eddy</b>
Drilling Contractor	<b>S &amp; B Drlg</b>		Type of Equipment <b>Rotary 9/16/81</b>		

\* witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
* 9 1/2	7"	17#		1100	360 Sx Circ
6 1/4	4 1/2	9.5#		1600	200 Sx Circ

Casing Data:

Surface \_\_\_\_\_ joints of \_\_\_\_\_ inch \_\_\_\_\_ # Grade \_\_\_\_\_  
(Approved) (Rejected) \_\_\_\_\_

Inspected by \_\_\_\_\_ date \_\_\_\_\_

Cementing Program

Size of hole 9 7/8" Size of Casing 7" Sacks cement required 290

Type of Shoe used guide Float collar used inst Btm 3 jts welded yes

TD of hole 1092 Set 1100 Feet of 7 Inch 17 # Grade \_\_\_\_\_

New-used csg. @ 1092 with 160 sacks neat cement around shoe w/ 2% CaCl.  
+ \_\_\_\_\_ sax \_\_\_\_\_ additives \_\_\_\_\_

Plug down @ 8:30 (AM) (PM) Date 9/21/81

Cement circulated NO No. of Sacks \_\_\_\_\_

Cemented by HALLIBURTON Witnessed by LARRY BROOKS

Temp. Survey ran @ 2:30 (AM) (PM) Date 9/21/81 top cement @ 500'

Casing test @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method Used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Checked for shut off @ \_\_\_\_\_ (AM) (PM) Date \_\_\_\_\_

Method used \_\_\_\_\_ Witnessed by \_\_\_\_\_

Remarks: TAGGED w/ 1" @ 496'. Pumped 130 sxs. Cl. C neat.

& circulated 30 sxs. to the pit.