

WORKOVER PROCEDURE DETAILS - CEMENTING

TREATMENT PARAMETERS (To be filled out after leak determination)

Problem: Csg Leak 7131-7136

Method: Use cmt retainer SA 7030. 100' cmt in annulus. Leave cmt/ret in hole.

CEMENT PROPERTIES

STAGE 1

30 sx Class C cmt, 1.32 cu. ft/sk, 14.8 ppg

Mix Water 6.3 gal/sk

Max Free Wtr 0 %

Fld Loss 125 cc/30 min @ 100 BHCT Thickening Time 5 hrs @ 50 BU

DRAFT 20690156