

Robinson Gas Com #1  
Form C-105  
Page 2

32. Acid, Shot, Fracture, Cement Squeeze, Etc.

| <u>Depth Interval</u> | <u>Amount &amp; Kind Material Used</u>                                                                                          |
|-----------------------|---------------------------------------------------------------------------------------------------------------------------------|
| 9265'                 | Squeeze cmt'd w/750 sx Cl C Thik-set cont'g $\frac{1}{2}$ # flocele/sk, 15# Gilsonite/sk & 2% CaCl followed by 150 sx Cl C Neat |
| 9110-9112'            | Squeeze cmt'd w/50 sx Cl H, .3% Halad 9 followed by 50 sx Cl H Neat                                                             |
| 9179-84'              | Squeeze cmt'd w/100 sx Cl H cont'g .5% Halad 9 followed by 50 sx Cl H Neat                                                      |
| 6482-6496'            | 4000 gals 15% HCL-LSTNE w/iron sequestrant                                                                                      |
| 6482-6496'            | Squeeze cmt'd w/100 sx Cl C cont'g .5% Halad 9 followed by 100 sx Cl C Neat                                                     |