

PROJECT NO.: 8-20-96
DATE: 8-20-96
PRESSURE: 3000 PSI
TEMPERATURE: 80

CEMENT: 301

ULTRASONIC
CEMENT ANALYZER
HALLIBURTON SERVICES

INITIAL SET: 50 @ 1:27
STRENGTH 1: 500 @ 4:52
STRENGTH 2: 1999 @ 24:25
CURR. STR.: 1325 @ 24:25

COMPRESSIVE STRENGTH (psi)

