

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Leatherstone Dev. Corp.</u>		Lease <u>Platt</u>		Well # <u>2</u>	
Location of Well	Unit	Section <u>26</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor <u>WEK</u>	Type of Equipment <u>Rotary - Re-entry</u>				

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>7 7/8"</u>	<u>5 1/2</u>	<u>15.50</u>	<u>used</u>	<u>2100'</u>	<u>Circ</u>

Casing Data:

Surface 60 joints of 5 1/2 inch 15.50 # Grade API used J-55
(Approved) (Rejected)

Inspected by Lelan Mearns date 5-10-76

Cementing Program

Size of hole 7 7/8" Size of Casing 5 1/2 Sacks cement required 575

Type of Shoe used Guide Float collar used Insert Btm 2 jts ~~welded~~ Thread Lock

TD of hole 1875 KB Set 1865' Feet of 5 1/2 Inch 15.50 # Grade J-55

New-used csg. @ 1865' with 475 sacks neat cement around shoe 50-50 POZ. 6 Salt
100 sack Howards additives .6% CFR-2

Plug down @ 8:45 (AM) (PM) Date 5-10-76

Cement circulated Yes No. of Sacks 75/50

Cemented by Halliburton Witnessed by Lelan Mearns

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: