

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Galtie Petr Corp</i>		Lease <i>Mallard H M</i>		Well # <i>1</i>	
Location of Well	Unit <i>L</i>	Section <i>28</i>	Township <i>18</i>	Range <i>26</i>	County <i>Eddy</i>
Drilling Contractor			Type of Equipment <i>Reverse bit 2-14-77</i>		
APPROVED CASING PROGRAM					
* <i>Witness</i>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
8 1/8"	8 5/8"	<i>24</i>		<i>1271</i>	<i>air, 1961</i>
<i>7 7/8"</i>	<i>5 1/2"</i>	<i>15.5</i>		<i>3000</i>	<i>air.</i>
Casing Data:					
Prod <i>72</i> joints of <i>5 1/2</i> inch <i>15 1/2</i> # Grade <i>J-55</i>					
☒ (Approved) (Rejected)					
Inspected by <i>Mike Williams</i> date <i>5/2/77</i>					
Cementing Program					
Size of hole <i>7 7/8</i> Size of Casing <i>5 1/2</i> Sacks cement required					
Type of Shoe used <i>Guide</i> Float collar used <i>2900</i> Btm 3 jts welded <i>Yes</i>					
TD of hole <i>3000</i> Set <i>2900</i> Feet of <i>5 1/2</i> Inch <i>15 1/2</i> # Grade <i>J-55</i>					
☒ New used csg. @ <i>2900</i> with <i>500</i> sacks neat cement around shoe					
+ <i>—</i> sax <i>—</i> additives <i>4/10 & 1 % CFR-Z + 2 % CC.</i>					
Plug down @ <i>5:10</i> (AM) (PM) Date <i>5/2/77</i>					
Cement circulated <i>No</i> No. of Sacks					
Cemented by <i>Halliburton</i> Witnessed by <i>Mike Williams</i>					
Temp. Survey ran @ (AM) (PM) Date top cement @					
Casing test @ (AM) (PM) Date					
Method Used Witnessed by					
Checked for shut off @ (AM) (PM) Date					
Method used Witnessed by					
Remarks: <i>Ran Weight bar down 5 1/2 + 8 5/8" annulus + tagged top of cement @ 495'</i>					