

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>PAN-AMERICAN PETCORP.</u>		Lease <u>STATE "CE"</u>		Well # <u>2</u>	
Location of Well	Unit <u>I</u>	Section <u>16</u>	Township <u>18^S</u>	Range <u>27^E</u>	County <u>EDDY</u>
Drilling Contractor	<u>LEE DRILLING CO.</u>		Type of Equipment <u>ROTARY</u>		
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>11"</u>	<u>8 5/8"</u>	<u>24 #</u>	<u>NEW</u>	<u>1500</u>	<u>CIRCULATE</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>9.5 #</u>	<u>NEW</u>	<u>6100</u>	<u>TIE INTO SURFACE</u>
Casing Data:					
Surface <u>51</u> joints of <u>8 5/8</u> inch <u>24</u> # Grade <u>J.S. API. New</u>					
(Approved) (Rejected)					
Inspected by <u>LOBLEY</u> date <u>2-8-62</u>					
Cementing Program					
Size of hole <u>11</u> Size of Casing <u>8 5/8</u> Sacks cement required <u>345</u>					
Type of Shoe used <u>GUIDE</u> Float collar used <u>INSERT</u> Btm 3 jts welded <u>THRED-LOK</u>					
TD of hole <u>1494</u> Set <u>1494</u> Feet of <u>8 5/8</u> Inch <u>24</u> # Grade <u>J.S. API.</u>					
<u>New</u> used csg. @ <u>600</u> sacks not cement around shoe					
+ <u>27 GEL</u> and 200 lbs. of additives <u>INCOR</u> <u>2.5% Coleman Chalkite</u>					
Plug down @ <u>8:15</u> (AM) (PM) Date <u>2-10-62</u>					
Cement circulated <u>Yes</u> No. of Sacks <u>35</u>					
Cemented by <u>HALLIBURTON</u> Witnessed by <u>LOBLEY</u>					
Temp. Survey ran @ (AM) (PM) Date top cement @					
Casing test @ (AM) (PM) Date					
Method Used Witnessed by					
Checked for shut off @ <u>5:15</u> (AM) (PM) Date <u>2-11-62</u>					
Method used <u>600 # pressure</u> Witnessed by <u>LOBLEY</u> <u>O.K.</u>					
Remarks:					

1494
1221
1494
1494
4494
2988
3453834