

no turn

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>S. J. McVay Drilling Co. Inc.</u>		Lease <u>SEWARD UNIT</u>		Well # <u>I</u>	
Location of Well	Unit <u>1</u>	Section <u>11</u>	Township <u>15 S</u>	Range <u>26 E</u>	County <u>EDDY</u>
Drilling Contractor	<u>MCVAY DRILLING CO.</u>		Type of Equipment <u>ROTARY</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>11</u>	<u>8 5/8</u>	<u>22</u>	<u>NEW</u>	<u>1300</u>	<u>700</u>
<u>7 7/8</u>	<u>4 1/2</u>	<u>11.60</u>	<u>NEW</u>	<u>9200</u>	<u>2000</u>

Casing Data:

Surface 46 joints of 8 5/8 inch 24 # Grade J.S. API. NEW
(Approved) (Rejected)

Inspected by LOBLEY date 11-2-62

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 528

Type of Shoe used GUIDE Float collar used YES Btm 3 jts welded THRED-LOK

TD of hole 1256 Set 1256 Feet of 8 5/8 Inch 24 # Grade J.S. API.

New ~~used~~ csg. @ 1256 with 100 sacks neat cement around shoe
+ 700 sax INCOR additives 2% GEL and 1/4 # FLOCCLE PER SK.

Plug down @ 7:35 (AM) (PM) Date 11-2-62

Cement circulated NO REMARKS No. of Sacks none

Cemented by HALLIBURTON Witnessed by LOBLEY

Temp. Survey ran @ 2:15 (AM) (PM) Date 11-2-62 top cement @ 587' BELOW S.

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ 8:15 (AM) (PM) Date 11-2-62

Method used 800 # press. Witnessed by LOBLEY OK

Remarks: PIPE MEASURED FROM K.B. 12.5' A.L.S. PUMPED IN 212 sks neat + 2%

Calcium Chloride VIA 1" TUBING at 5:30 pm 11-2-62 did not circulate.

pumped in 200 sks. neat + 2% GEL + 3% calcium chloride + 1/4 # FLOCCLE per

sks. at 11:30 a.m. 11-2-62 Did not circulate. pumped in 100 sks

neat at 4:00 am 11-3-62 did not circulate. pumped in 50 sks

neat + 2% GEL + 1/4 # FLOCCLE at 10:35 am 11-3-62 did not circulate.

Pumped in 200 sks neat + 2% GEL + 2% cal. + 1/4 # floccle per sk. at 2:30 pm

11-3-62. Cement circulated but fell back down hole a few feet. then poured

in 4 yds. ready mix with pea gravel which completed circulation.

amen!

$$\begin{array}{r} 2 \ 5 \ 7 \ 9 \\ \hline 1 \ 4 \ 4 \\ 2 \ 1 \ 2 \\ \hline 11 \ 11 \end{array}$$

$$\begin{array}{r} 5 \ 0 \ 5 \\ \hline 8 \ 4 \ 9 \\ \hline 3 \ 7 \ 1 \ 2 \ 5 \ 1 \ 2 \\ \hline 7 \ 5 \ 2 \ 1 \ 0 \ 4 \ 8 \ 7 \ 6 \ 0 \\ \hline 2 \ 1 \ 5 \ 7 \ 1 \ 2 \\ \hline 1 \ 2 \ 5 \ 6 \\ \hline 3 \ 7 \ 5 \ 2 \end{array}$$