

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <i>Waters Pet. Corp.</i>		Lease <i>Yates AS Fee</i>		Well # <i>1</i>	
Location of Well	Unit <i>23105+u^K</i>	Section <i>25</i>	Township <i>18</i>	Range <i>25</i>	County <i>Eddy</i>
Drilling Contractor <i>Pennsylvania & Co.</i>	Type of Equipment <i>Rotary</i>				
<u>APPROVED CASING PROGRAM</u> <i>1600 SH approved 2-16-66</i>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<i>6 3/4</i>	<i>4 1/2</i>	<i>9.5</i>		<i>1100</i>	<i>Circ. to surface</i>
Casing Data:					
Surface <i>37</i> joints of <i>4 1/2</i> inch <i>9.5</i> # Grade <i>J</i>					
(Approved) (Rejected)					
Inspected by <i>R. L. Lamm</i> date <i>3-4-66</i>					
Cementing Program					
Size of hole <i>6 3/4</i> Size of Casing <i>4 1/2</i> Sacks cement required					
Type of Shoe used <i>float</i> Float collar used Btm 3 jts welded					
TD of hole <i>1166</i> Set <i>1165</i> Feet of <i>4 1/2</i> inch <i>9 1/2</i> # Grade <i>J</i>					
New-used csg. @ <i>1165</i> with <i>50</i> sacks neat cement around shoe					
+ <i>150</i> sax <i>270 gal.</i> additives					
Plug down @ <i>1100</i> (AM) (PM) Date <i>3-5-66</i>					
Cement circulated <i>400</i> No. of Sacks					
Cemented by <i>Waters</i> Witnessed by <i>Waters</i>					
Temp. Survey ran @ (AM) (PM) Date top cement @					
Casing test @ (AM) (PM) Date					
Method Used Witnessed by					
Checked for shut off @ (AM) (PM) Date					
Method used Witnessed by					
Remarks: <i>used 2 cement bags on the spot - cement fell back 10-12' in 30"</i>					
<i>Checked 4 hrs later down near 100' to 110' of ready mix</i>					
<i>3-7-66 fell to surface 110' 120' seal with sand - cement @ 9:15 AM</i>					

ILLEGIBLE