

will file

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u> Yates Pet. Corp </u>		Lease <u> Hornbaker BH </u>		Well # <u> 1 </u>	
Location of Well	Unit <u> G </u>	Section <u> 25 </u>	Township <u> 18 </u>	Range <u> 25 </u>	County <u> Eddy </u>
Drilling Contractor <u> 1900 N 1650 E </u>			Type of Equipment <u> Rotary </u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u> 13 3/4 </u>	<u> 9 5/8 </u>	<u> 32.3 H40 </u>	<u> NEW </u>	<u> 1000 </u>	<u> Circ </u>
<u> 8 3/4 </u>	<u> 7 </u>	<u> 14# H40 </u>		<u> 2150 </u>	<u> 150 / into 9 5/8 </u>

Casing Data:

Surface 36 joints of 7 5/8 inch 32.3 # Grade H
(Approved) (~~Rejected~~)

Inspected by R. L. L. date 2-15-67

Cementing Program

Size of hole 13 3/4 to 8 3/4 Size of Casing 9 5/8 Sacks cement required

Type of Shoe used Float Float collar used Btm 3 jts welded Thred Lok

TD of hole 1080 Set 1077 Feet of 9 5/8 Inch 32.3 # Grade H

New-used csg. @ with 100 C sacks neat cement around shoe

+ 400 sax C 2% gel additives

Plug down @ 5:00 (AM) (PM) Date 2-15-67

Cement circulated NO No. of Sacks

Cemented by Witnessed by

Temp. Survey ran @ 1:30 (AM) (PM) Date 2-16-67 top cement @ 200 +

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks:

Date	Time	Log Depth	Sacks
<u> 1-16-67 </u>	<u> 4:30 AM </u>	<u> 230 </u>	<u> 100 C 4% CaCl, 140 C neat no returns </u>
<u> " </u>	<u> 7:45 AM </u>	<u> 170 </u>	<u> 100 C 4% CaCl no returns </u>
<u> " </u>	<u> 10:00 AM </u>	<u> 190 </u>	<u> 100 C 4% CaCl, 50 C neat go circulation </u>
<u> " </u>	<u> 1:00 PM </u>	<u> 30 </u>	<u> 60 C neat cement circulated </u>