

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Yates Pet Corp</u>		Lease <u>Nix-Curtis B H</u>		Well # <u>Z - P</u>	
Location of Well	Unit	Section	Township	Range	County
		<u>25</u>	<u>18</u>	<u>25</u>	<u>Cddy</u>
Drilling Contractor <u>9905 330 E</u>			Type of Equipment <u>Rotary</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>9 1/2</u>	<u>7</u>	<u>26</u>	<u>NEW</u>	<u>1100</u>	<u>Circ.</u>
<u>6 1/4</u>	<u>4 1/2 - 5 1/2</u>	<u>95.14</u>		<u>1700</u>	<u>Line</u>

Casing Data:

Surface joints of 7 inch # Grade J
(Approved) (Rejected)

Inspected by J. J. Lumb date 1-24-68

Cementing Program

Size of hole 12 1/2 - 403 Size of Casing 7 Sacks cement required

Type of Shoe used Tepe Float collar used No Btm 3 jts welded No

TD of hole 1100 Set Feet of Inch # Grade

New-used csg. @ 1100 with 50 sacks neat cement around shoe

+ 300 sax class C additives 2% gel 1 2/3 # flocc 1.6 #/sac gilsonite

Plug down @ 11:00 (AM) (PM) Date 1-24-68

Cement circulated No No. of Sacks

Cemented by Denton Witnessed by Sturman

Temp. Survey ran @ 7:45 (AM) (PM) Date 1-25-68 top cement @ 510

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Could not get tubing below 150'. Tried all sides of hole, spudded, twisted and pumped, did not go. One centralizer on shoe.

Date	Time	Cement	Floccle	CaCl ₂	Fill
1-25-68	1:10PM	100 C	50# Floccle	4%	25'
	4:45PM	100 C	50# Floccle	4%	To 83' FL up from 150 To 90'

M.D. W. 1 Ten yards