

NEW MEXICO OIL CONSERVATION OF FUEL
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Cement Co. Inc.</u>		Class <u>Class. No.</u>		Well #	
Location of Well	Unit <u>Area</u>	Section	Township	Range	County
Drilling Contractor			Type of Equipment <u>Rotary & start approx 10-1-72</u>		
APPROVED CASING PROGRAM 9-8-72 <u>** Witness</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>2 1/2"</u>	<u>11"</u>	<u>65</u>		<u>200</u>	<u>200</u>
<u>1 1/2"</u>	<u>11 3/4"</u>	<u>42</u>		<u>1200</u>	<u>875</u>
<u>1 1/2"</u>	<u>11 3/4"</u>	<u>42</u>		<u>1000</u>	<u>365</u>
<u>1 1/2"</u>	<u>11 3/4"</u>	<u>42</u>		<u>9500</u>	<u>250</u>
Casing Data:					
Surface <u>28</u> joints of <u>11 3/4</u> inch <u>42</u> # Grade <u>API New H-40</u>					
(Approved) (Rejected)					
Inspected by <u>A. C. Miller</u> date <u>9-29-72</u>					
Cementing Program					
Size of hole <u>1 1/2</u> Size of Casing <u>11 3/4</u> Sacks cement required <u>875</u>					
Type of Shoe used <u>Guide</u> Float collar used <u>Insert Btm 3 jts welded & Thrued Lock</u>					
TD of hole <u>11950</u> Set <u>1183</u> Feet of <u>11 3/4</u> Inch <u>42</u> # Grade <u>H-40 New API</u>					
New-used csg. @ _____ with <u>100/5x</u> sacks neat cement around shoe <u>H 2% CC 15.5</u>					
+ <u>77 1/2</u> sax <u>2% Gel</u> additive <u>2% CC</u> <u>14.7</u>					
Plug down @ <u>2:00</u> (AM) (PM) Date <u>9-30-72</u>					
Cement circulated <u>Yes</u> No. of Sacks <u>290/5x - 586615</u>					
Cemented by <u>Halliburton</u> Witnessed by <u>A. C. Miller</u>					
Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____					
Casing test @ _____ (AM) (PM) Date _____					
Method Used _____ Witnessed by _____					
Checked for shut off @ _____ (AM) (PM) Date _____					
Method used _____ Witnessed by _____					
Remarks: <u>193.87</u> <u>4 KB 16"</u> <u>20" Hole</u> <u>Csg. 65" H-40</u> <u>Set 1183</u>					
<u>Cemented with 1.50/5x Type H 4% gel 2% CC 100/5x Type H 2% CC</u>					
<u>Plug down 4:00 A.M. Cement did cure</u>					