

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER 110
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator Coquina Oil Corp.		Lease Claney Cam		Well # 1	
Location of Well	Unit 0	Section 11	Township 18	Range 25	County Eddy
Drilling Contractor			Type of Equipment		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
17 1/4"	13 7/8	61#		500	500/sx Circ
12 1/4"	8 5/8	24#		1300	850/sx Circ
7 7/8"	4 1/2	10.5-11.6		9000	

Casing Data:

Surface 38 joints of 2 7/8 inch 24 # Grade Used K-55 API
(Approved) (Rejected) -

Inspected by L. A. Mearns date 3-26-73

Cementing Program

Size of hole 12 1/4 TD Size of Casing 8 5/8 Sacks cement required 600/sx

Type of Shoe used Texas Pattern Float collar used Insert Btm 3 jts welded Partial Link

TD of hole 1300 KB 1290 GL Feet of 2 7/8 inch 24 # Grade K-55 API Used

New-used csg. @ 1290' with 150 sacks neat cement around shoe class C 2% CC 14.8
+ 450 /sax Halco Lite additives 4# Flo-Sol 5# Silicate 13.0

Plug down @ 2100 (~~AM~~) (PM) Date 3-26-73

Cement circulated 489 No. of Sacks 25

Cemented by McClintock Witnessed by L. A. Mearns

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: TD 504 KB 13jts 13 7/8 48# STC API New, Texas Pattern

Build shoe, 400/sx Halco Lite 13.7/100/sx Class C 2% CC 4# Flo-Sol 14.2

Plug down 2:30 A.M. 3-24-73 Case 100/sx