

STATE OF NEW MEXICO
DRAWER 10
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>David Farker</u>		Lease <u>Mary F. Brannan</u>		Well # <u>1</u>	
Location of Well	Unit <u>165000</u>	Section <u>3</u>	Township <u>18</u>	Range <u>26</u>	County <u>El Paso</u>
Drilling Contractor <u>Walter G. Galya</u>			Type of Equipment <u>Rotary 2 1/2" 4" 7-3 73</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>17 1/2"</u>	<u>13 3/8"</u>	<u>48</u>		<u>500</u>	<u>350 ccs</u>
<u>12 1/2"</u>	<u>8 5/8"</u>	<u>20</u>		<u>1300</u>	<u>600</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>10.5 x 11.6</u>		<u>900</u>	<u>450</u>

Casing Data:

Surface _____ joints of 8 5/8" inch 2-1 # Grade API No. K-55
(Approved) (~~Rejected~~)

Inspected by A. C. McLean date 7-13-73

Cementing Program

Size of hole 12 1/2" 1132 ^{11" 1350} Size of Casing 8 5/8" Sacks cement required _____

Type of Shoe used Anchor Float collar used Insert Btm 3 jts welded Yes

TD of hole 1380 Set _____ Feet of 8 5/8" inch 2-1 # Grade K-55

New-used csg. @ _____ with _____ sacks neat cement around shoe

+ _____ sack _____ additives _____

Plug down @ _____ (AM) (PM) Date _____

Cement circulated 1/2 No. of Sacks None

Cemented by Nallibacter Witnessed by _____

Temp. Survey ran @ _____ (AM) (PM) Date _____ top cement @ _____

Casing test @ _____ (AM) (PM) Date _____

Method Used _____ Witnessed by _____

Checked for shut off @ _____ (AM) (PM) Date _____

Method used _____ Witnessed by _____

Remarks: Can 13 3/8" 48" 11-110 API No. TD 475 KB set 460 RL

300/sx Horse tail 1/2" float 2% CC 13.4 - 13.9 100/sx (Horse) 2% CC

14.5 PD 8:48 AM Did not Circ Temp down 110 1:00 PM 7-11-73

Can inch 150/sx (Horse) 2% CC down 3:30 PM Circ 15/sx