

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Anadarko Prod Co.</u>		Lease <u>Artesia 8th T29.</u>		Well # <u>1</u>	
Location of Well	Unit <u>A</u>	Section <u>23</u>	Township <u>18</u>	Range <u>27</u>	County <u>Eddy</u>
Drilling Contractor	<u>10' FNL 1310' FEL</u>		Type of Equipment <u>Rotary</u>		
<u>WEK</u>					

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>12 3/4"</u>	<u>8 5/8</u>	<u>24</u>	<u>API</u>	<u>300'</u>	<u>Circ</u>
<u>7 7/8"</u>	<u>4 1/2</u>	<u>10.5</u>	<u>API</u>	<u>2000'</u>	<u>Circ</u>

Casing Data:

Surface 7 joints of 8 5/8 inch 24 # Grade API New K-55
(Approved) (~~Rejected~~)

Inspected by L. Mermis date 2-10-75

Cementing Program

Size of hole 12 1/4 Size of Casing 8 5/8 Sacks cement required 160

Type of Shoe used Guide Float collar used None Btm 2 jts welded

TD of hole 304' KB Set 294 Feet of 8 5/8 Inch 24 # Grade K-55

New-used csg. @ 294' GL with 160 sacks neat cement around shoe Class C 2 1/2 cc 14.8
+ sax additives

Plug down @ 8:45 (AM) (PM) Date 2-10-75

Cement circulated No No. of Sacks None

Cemented by Dowell Witnessed by L. Mermis

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Lost 300' to be filled to surface with
Ready mix.

7 7/8" hole TD 2009' KB Set 2000' GL Ran 55 1/2 4 1/2" 10.5 J-55 API New
Float shoe, Cnt 426/sx Class C 4% Gel 2% cc 1/4" Cello Flake 12.6 #
355/sx Class H. 2% D-65, 5# Salt or D-44, 10# Sand per sx 16.0 #