

THE MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>DAVID FASKEN</u>		Lease <u>BRADSHAW</u>		Well # <u>1</u>	
Location of Well	Unit <u>G</u>	Section <u>2</u>	Township <u>18 S</u>	Range <u>26-E</u>	County <u>EDDY</u>
Drilling Contractor	<u>WARTON DRILLING CO</u>		Type of Equipment <u>ROTARY</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>30</u>	<u>20"</u>	<u>91.4#</u>		<u>35'</u>	<u>READY-MIX</u>
<u>17 1/2</u>	<u>13 3/8</u>	<u>48#</u>		<u>1300'</u>	<u>1250 CIRC</u>
<u>12"</u>	<u>8 3/8</u>	<u>28#</u>		<u>1800'</u>	<u>250 SX</u>

Casing Data:

~~INTER~~ 42 joints of 8 3/8 inch 24 # Grade J-55 STEEL API RING 3
(Approved) (~~Rejected~~) CENT. G 1878, 1812, 1758, 1371, & 1327.

Inspected by James D. Bingham date FEB. 10-75

Cementing Program

Size of hole 12 1/4 Size of Casing 8 3/8 Sacks cement required 250

Type of Shoe used GUIDE Float collar used INSERT Btm 3 jts welded THREADED

TD of hole 1900 K.B. Set 1825 G.L. Feet of 8 3/8 Inch 24 # Grade J-55 STEEL API RING 3

New ~~used~~ csg. @ 1885 G.L. with 320 sacks neat cement around shoe

+ sax additives 2 1/2 CA C₁₂

Plug down @ 2:00 (AM) (PM) Date 2-16-75

Cement circulated NO No. of Sacks 7

Cemented by HOWCO Witnessed by James D. Bingham

Temp. Survey ran @ 7:00 (AM) (PM) Date 2-14-75 top cement @ 1818'

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: SURFACE CSG. RAN 35 JTS, 13 3/8 X 48#, 54.5# & 41#, J-55 & K-55

NEW RANGE 2 & RANGE 3 CSG. SET @ 1316 K.B., 1331 G.L. w/ CENT'S AT 1312 1/2'

1198' GUIDE SHOE ON BOTTOM, INSERT FLOAT AT CP 1 1/2" ST. CMTD w/ 800 SX

HOWCO LITE w/ 1/4" FROELED 2 1/2" CA C₁₂, FOLLOWED WITH 250 SX (CLASS C)

w/ 2 1/2" CA C₁₂. CIRC EST 100 BLS CEMENT TO PIT. PD 11:35 PM 2-13-75.