

NEW MEXICO OIL CONSERVATION COMMISSION  
DRAWER DD  
ARTESTIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Atlantic Richfield Co</u>		Lease <u>Empire Abo Unit 2</u>		Well # <u>141</u>	
Location of Well	Unit <u>N</u>	Section <u>2</u>	Township <u>18</u>	Range <u>27</u>	County <u>Eddy</u>
Drilling Contractor		Type of Equipment			
		<u>Rotary</u>		<u>CACTUS -</u>	
				<u>1100 or 14B. To GL</u>	
<u>APPROVED CASING PROGRAM</u>					
Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>11"</u>	<u>8 7/8"</u>	<u>24# K-55</u>		<u>1000'</u>	<u>375 circ</u>
<u>7 7/8"</u>	<u>5 1/2"</u>	<u>14# K-55</u>		<u>6150'</u>	<u>1050 circ</u>
Casing Data:					
Surface <u>27</u> joints of <u>8 7/8</u> inch <u>24</u> # Grade <u>K-55</u>					
(Approved) ( <del>Rejected</del> )					
Inspected by <u>Leon Bergeton</u> date <u>6-17-75</u>					
Cementing Program					
Size of hole <u>11</u> Size of Casing <u>8 7/8</u> Sacks cement required <u>192</u>					
Type of Shoe used <u>Guide</u> Float collar used <u>YES</u> Btm 3 jts welded <u>YES</u>					
TD of hole <u>1000'</u> Set <u>1005</u> Feet of <u>8 7/8</u> Inch <u>24</u> # Grade <u>K-55</u>					
New-used csg. @ <u>98961</u> with <u>150</u> sacks neat cement around shoe					
+ <u>350</u> sax <u>CLASS</u> additives <u>8# SALT, 1/4# CEMENT</u>					
Plug down @ <u>115</u> (AM) ( <del>PM</del> ) Date <u>6-17-75</u>					
Cement circulated <u>NO</u> No. of Sacks <u>192</u>					
Cemented by <u>B.I.</u> Witnessed by <u>Leon Bergeton</u>					
Temp. Survey ran @ <u>730</u> (AM) ( <del>PM</del> ) Date <u>6-17-75</u> top cement @ <u>120'</u>					
Casing test @ <u>-</u> (AM) (PM) Date <u>-</u>					
Method Used <u>-</u> Witnessed by <u>-</u>					
Checked for shut off @ <u>-</u> (AM) (PM) Date <u>-</u>					
Method used <u>-</u> Witnessed by <u>-</u>					
Remarks: <u>-</u>					