

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Wm. G. Ross</u>		Lease <u>A.G. Rogers com.</u>		Well # <u>1</u>	
Location of Well	Unit <u>6605-6608</u>	Section <u>3</u>	Township <u>18</u>	Range <u>26</u>	County <u>El Paso</u>
Drilling Contractor	<u>Morano Rig 5</u>		Type of Equipment <u>Rotary test 6-26-75</u>		

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>36"</u> <u>17 1/2"</u>	<u>20"</u> <u>13 3/8"</u>	<u>48</u>		<u>40'</u> <u>1250+</u>	<u>1050 circulated</u>
<u>12 1/4"</u>	<u>8 7/8"</u>	<u>24</u>		<u>200</u>	<u>350 700-1150</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>11.60</u>		<u>9200</u>	<u>450</u>

Casing Data:

Surface 31 joints of 13 3/8 inch 48 # Grade API New 4-40
(Approved) (~~Rejected~~)

Inspected by Lelan Merms date 6-27-75

Cementing Program

Size of hole 17 1/2" Size of Casing 13 3/8 Sacks cement required 1550/54

Type of Shoe used Insert Float collar used Insert Btm 2 jts ~~welded~~ Threadlock

TD of hole 1350 KB Set 1368 GL Feet of 13 3/8 inch 48 # Grade 4-40

New-used csg. @ 1368 GL with 250 sacks neat cement around shoe Class C 2% cc 14.8
+ 1300 sack Newco Lite additives 6# Gilsomite 4# Floet 2% cc 13.0"

Plug down @ 12:30 (AM) (PM) Date 6-28-75

Cement circulated 1/2 No. of Sacks 250

Cemented by Halliburton Witnessed by Lelan Merms

Temp. Survey ran @ (AM) (PM) Date top cement @

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: Water 72'-200' 543'-675' 713'-21' 741' 60' 780'-812' 1168-1282

Lat Cur 170'

Test TD 1937 KB Set 1925 GL Run 4746 8 5/8" 24# API New K-55

11" hole Cmt 375/sx Newco Lite 4# Floet 5# Gilsomite, 200/sx Class C 2% cc