

NEW MEXICO OIL CONSERVATION COMMISSION
DRAWER DD
ARTESIA, NEW MEXICO

FIELD REPORT FOR CEMENTING OF WELLS

Operator <u>Depco Inc.</u>		Lease <u>Serry-Evans Com.</u>		Well # <u>1</u>	
Location of Well	Unit <u>480.~ 1880e</u>	Section <u>24</u>	Township <u>18</u>	Range <u>26</u>	County <u>Eddy</u>
Drilling Contractor <u>Maranco</u>			Type of Equipment <u>Rotary to start approx. 9-1-75</u>		

* witness

APPROVED CASING PROGRAM

Size of Hole	Size of Casing	Weight Per Foot	New or Used	Depth	Sacks Cement
<u>20"</u>	<u>16"</u>	<u>65#</u>		<u>200</u>	<u>350 cwt.</u>
* <u>15"</u>	<u>11 3/4"</u>	<u>42</u>		<u>1000</u>	<u>750 "</u>
* <u>11"</u>	<u>8 5/8"</u>	<u>24</u>		<u>2000</u>	<u>750 "</u>
<u>7 7/8"</u>	<u>4 1/2"</u>	<u>11.6</u>		<u>9560</u>	<u>350</u>

Casing Data:

Surface 34 joints of 11 3/4 inch 42 # Grade 3000 Tested Csg
New (Approved) (~~Rejected~~)

Inspected by John Merriam date 10-1-75

Cementing Program

Size of hole 15" Size of Casing 11 3/4" Sacks cement required 510

Type of Shoe used Grade Float collar used Insert Btm 2 jts welded Thread Lock

TD of hole 1010' KB Set 998' 2" Feet of 11 3/4 inch 42 # Grade New Tested

New-used csg. @ 998' 2" with 150 sacks neat cement around shoe class C 2% CC 4.8
+ 360 sax class C 2% CC additives 2% bence 4" Cello flake 6" salt 5" 2/3omite

Plug down @ 6125 (AM) (PM) Date 10-1-75

Cement circulated No No. of Sacks None

Cemented by BJ Witnessed by John Merriam

Temp. Survey ran @ 1130 (AM) (PM) Date 10-2-75 top cement @ 360

Casing test @ (AM) (PM) Date

Method Used Witnessed by

Checked for shut off @ (AM) (PM) Date

Method used Witnessed by

Remarks: SURF CSG 16" x 54" H-40 SET @ 207' CMTD W/ 250 Sx CLASS "C"

2% CaCl₂ - PLUG DOWN 10²⁰ PM FILLED ANNULUS WITH 1 1/2 YARDS READY-MIX

Ran 1" to 347' and tugged out 150 Sx Class C 4% CC

Cure 10/30 PD 3:30 PM